

Specification	
Specification Number	59000
Species	Hickory/Pecan
Hardness/Janka	1820
Construction	Engineered
Wear Layer	4mm
Thickness	5/8"
Width	5"
Lengths	18" – 96" Random length
Cut	Plain Sawn
Grade	Select
Finish	UV Urethane
Field Applied	No
VOC Compliant	N/A
Certifications available upon request	FloorScore®, FSC, & HPD

Installation: Please specify as a turnkey (installed) product by Woodwright Hardwood Floor Company to insure correct installation. In projects outside our labor service area, please make note of these important installation guidelines.

- Moisture test the slab with (1) calcium chloride test per 1000 SF. If moisture readings are over 3 lbs per SF, then a moisture barrier will be required.
 - Bostik MVP4 moisture barrier is our recommendation.
- Flatten slab to a tolerance of ¼" in 10' using cement based floor leveler.
- Direct glue flooring planks to subfloor using polyurethane adhesive such as Bostik BST or equal.
- Protect wood floor with ramboard or hardboard over kraft paper.
- 5 day acclimation period required prior to installation. Once flooring is direct glued and finished, it is also vital to maintain the HVAC Envelope to a +/- 5% Relative Humidity within the NWFA recommended range. Failure to follow these guidelines could void warranty.

Cut: Please note that Pecan & Hickory are one in the same according to NHLA and Woodwright does not make a distinction between them. The Characteristics of the specie are as follows:

- Large amount of natural color variation caused by the inherent mixture of heartwood and sapwood
- Black marks and streaks allowable even in the select grade.

Warranty: As intended for horizontal wood floor applications, the product offers a lifetime structural warranty and 1 year light commercial warranty on the shop applied finish.

Images: For additional images, please contact us at sales@woodwright.net.

